



## PESO TEÓRICO Kg/m COBRE

Pulgada	mm	Circular	Cuadrada	Hexagonal
1/8	3.18	0.07	0.09	0.08
3/16	4.76	0.16	0.20	0.17
1/4	6.35	0.28	0.36	0.31
5/16	7.94	0.44	0.56	0.49
3/8	9.53	0.63	0.81	0.70
7/16	11.11	0.86	1.10	0.95
1/2	12.70	1.13	1.44	1.24
9/16	14.29	1.43	1.82	1.57
5/8	15.88	1.76	2.24	1.94
11/16	17.46	2.13	2.71	2.35
3/4	19.05	2.54	3.23	2.80
13/16	20.64	2.98	3.79	3.28
7/8	22.23	3.45	4.40	3.81
15/16	23.81	3.96	5.05	4.37
1	25.40	4.51	5.74	4.97
1 1/16	26.99	5.09	6.48	5.61
1 1/8	28.58	5.71	7.27	6.29
1 3/16	30.16	6.36	8.10	7.01
1 1/4	31.75	7.05	8.97	7.77
1 5/16	33.34	7.77	9.89	8.57
1 3/8	34.93	8.53	10.86	9.40
1 7/16	36.51	9.32	11.87	10.28
1 1/2	38.10	10.15	12.92	11.19
1 9/16	39.69	11.01	14.02	12.14
1 5/8	41.28	11.91	15.16	13.13
1 11/16	42.86	12.84	16.35	14.16



Pulgada	mm	Circular	Cuadrada	Hexagonal
1 ¾	44.45	13.81	17.58	15.23
1 13/16	46.04	14.82	18.86	16.3
1 7/8	47.63	15.85	20.19	17.48
1 15/16	49.21	16.93	21.55	18.67
2	50.80	18.04	22.97	19.89
2 ¼	57.15	22.83	29.07	25.17
2 ½	63.50	28.19	35.89	31.08
2 ¾	69.85	34.10		
3	76.20	40.59		
3 ½	88.90	55.24		
4	101.60	72.16		